

Cléophanie Brochard-Richard

Chen Wei, Anis Chiout, Aymen Mahmoudi, Fabrice Oehler, Abdelkarim Ouerghi, Federico Panciera, Julien Chaste

C2N, 10 boulevard Thomas Gobert, Palaiseau, France

cleophanie.brochard@c2n.upsaclay.fr

Heat transport in h-BN

2D materials have new and intriguing properties, including their thermal properties. Like 3D materials, there is a wide variety of 2D materials with all ranges of thermal conductivity that can be simply assembled on top of each other [1]. Moreover, the thermal conductivity is extremely anisotropic in these materials. It has been demonstrated in the same 2D heterostructures ratios of 3 orders of magnitude between vertical and in-plane thermal conductivity, a record. Moreover, the interest from a fundamental point of view is the appearance at room temperature of a particular regime of phonon scattering, which allows to describe the heat transport as a hydrodynamic flow [2]. Thanks to these characteristics, it is interesting to study their thermal properties.

Here, we focus on the thermal conductivity of suspended h-BN. It is an interesting material because it has a very high thermal conductivity but is electrically insulating. Nevertheless, it is difficult to heat it with a laser because of its low absorbance. To overcome this problem and to perform thermal mapping, we have made two heating bridges of Silicon between which a flake of hBN is suspended. One of the bridges is heated by Joule effect while the other one allows us to calibrate the heat flow through the 2D materials. Raman spectroscopy measurements allow to measure the temperature at each point of the system. We were able to extract a thermal conductivity of h-BN around 200°C equal to 420 W.m⁻¹.K⁻¹.

[1] Qian X et al. , Nat. Mater., 20 (2021), 1188-1202

[2] Shi L et al, Science, 364(2019), 332-333

Figures




Figure 1: a) b) Schematic sketch (a) and optical image (b) of the device structure with a suspended hBN between two silicon heaters. c) Temperature map of Silicon, measured with a green laser, when one electrode is hot. d) Temperature gradient of the 2D material between the two bridges (inset : Raman spectrum of WSe₂) All scales bar : 10 microns